

A-C[®] 400

Ethylene vinyl acetate (EVA) copolymer in prill form, with a VA content of 13%, used extensively in hot melt adhesives (HMAs) to control rheology and boost adhesion. It can be added as a diluent but provides the dual function of reducing application viscosity at melt, while providing an adhesion boost versus homopolymer, non functional diluents (FT, byproduct, thermally degraded (TD) and PE homopolymer waxes). It is completely miscible in EVA adhesive resins, as would be expected by the similar chemistry. It is also used in candles to provide paraffin crystal nucleation, which increases thermal and breakage resistance, adhesion to glass, and fragrance retention.

TYPICAL PROPERTIES

Property	Value
Hardness	9.5
Viscosity @ 140° C	595
Drop Point, Mettler	92°C(198°F)
Density	0.92
Vinyl Acetate Content	13% Vinyl Acetate

REGULATORY APPROVALS

Property	Value
Plastic Pipe Institute/NSF*	No
FDA Indirect Approvals*	Yes

PRODUCT FORM AND SIZE

Property	Value
Product Form	Prill

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

© 2019 Honeywell International Inc.

All rights reserved

